## Polyethylene Wax in Candles

ligh quality candles demanded by today's consumers often requires the use of additives to enhance properties of the base paraffin wax.

New techniques of manufacturing and crafting candles has also required that the properties of paraffin be enhanced to provide the best results both aesthetically and in burning of candles.

Marcus Low Molecular Weight Polyethylene wax is an ideal additive for enhancing the properties of paraffin wax used in candles.

Use of Marcus Polyethylene wax at a level of 1-4% can be used to improve the following properties of candles:

- Opacity
- Drip
- Color
- Scent
- Mold release
- Gloss
- Burning time
- Strenath

## **Marcus Wax Applications In Candles**

Marcus wax to enhance appearance and burning of candles

Opacity - Faraffin wax soften decirable to enhance the uniformity and reduce mottling appearance of candles by making them opaque. This can be accomplished with the addition of only a few percent by weight of Marcus wax

Drip- Typical paraffin's used in candles have melt points of 130-145<sup>±</sup> depending on the type candle being produced. Direct addition of a few percent Marcus wax to the paraffin will help reduce dripping. Another technique is to add a slightly higher level (up to 4%) of Marcus wax into paraftin that will be used as a veneer on the outer coating of the candle.

Color- As molten paraffin cools it forms crystals. Smaller crystal formation has the benefit of increasing oi and dye holding capacity of the paraffin. Dyes are often added to paraffin. Small quantities of Marcus wax, well dispersed in paraffin, will aid in nucleation of paraffin and formation of smaller crystals with enhanced color fixing capacity.

Scent- Scents that are accepted to candles are usually in the form of oils. Like colorants, the use of Marcus wax can help encapsulate scent oils and allow for more uniform release.

Mold release- polyethylene has good mold release properties due to its low surface energy property.

Gloss - Marcus Polyethylene waxes have good gloss and can impart a durable and attractive outer surface to candles. This can reduce surface b emishes due to handling and packaging.

Burning time-Burning rates depend on many factors including type of parafin, design of candle and wick characteristics. Addition of Marcus Polyethylene wax to parafin can extend candle life by reducing dripping and less puddling of the wax during burning.

Strength-Marcus Polyethylere waxes impart strength and durability to paraffin. This can be accomplished through use of an outer dip or dispersing







Most Marcus Polyethylene Waxes (M200, M300, & M500) have melting points well above that of traditional paraffins used in candle wax. To completely melt these grades of Marcus wax requires melting to temperatures in excess of 125 C. Proper dispersion of the Marcus wax in paraffin requires melt temperatures be maintained during mixing and dilution.

Safety should a ways be the number one consideration in making cancle. This applies to both safe manufacturing and safe burning of candles. The information contained herein is intended as a guideline - and not a substitute for safety training, education and well designed, manufactured and tested candles.

Marcus Cil & Chemical Division of H.R.D. Corporation PO Drawer 450267 Houston, TX 77245 U.S.A Fax 713-726-9885 Telephone: 800-Marcus\*

(800-627-2671 ) Email <u>cortactus@marcusoil.com</u>

Visit us at www.marcusoil.com