



# Marcus Oil & Chemical

Division of HRD Corporation

## Technical Data Sheet

### MARCUS NAT 155 WAX

**COMPOSTION: Hydrogenated Natural Oil**

#### TYPICAL PROPERTIES

Drop Melting Point (D-127)	155 - 160 Deg F.
Penetration (D-1321) @ 77 Deg. F.	2 max, dmm
@ 130 Deg. F.	19 max, dmm
Viscosity (D-3256) @ 300 Deg. F	5 - 10 cPs.
Saponification Value (mg / g)	180 - 185
Color	White
Form	Pastilles or Flakes

CAS NUMBER: 8016 – 70 – 4

NOTE: Production and application of hydrogenated natural oils is covered under US and international patents and patents pending including: US 6,811,824;US 6,890,982;US 7267743;US 8138250;US 7776928;US 7910758; US 8491778; US 8491777; US 8734725; US 8506888; US 8669401

*Superior Quality High Performance Additives*

14549 Minetta, Houston, TX 77035 USA P.O. Drawer 450267, Houston, TX 77245 USA  
713.721.9131 800.MARCUS 1 Fax 713.726.9885 E-mail [marcusoil@aol.com](mailto:marcusoil@aol.com) [www.marcusoil.com](http://www.marcusoil.com) Rev:10-2-14